



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number: **0 655 320 A1**

(12) **EUROPEAN PATENT APPLICATION**

(21) Application number: **94203317.6**

(22) Date of filing: **15.11.94**

(51) Int. Cl.⁶: **B29C 71/00, B29B 17/00,
C08J 11/06, C08L 67/02,
C08K 3/00, //B29K67:00,
B29K105:06, B29K105:26,
B29L16:00**

(30) Priority: **17.11.93 IT MI932442**

(43) Date of publication of application:
31.05.95 Bulletin 95/22

(84) Designated Contracting States:
BE DE FR GB NL SE

(71) Applicant: **Michelotti, Leopoldo**
Viale Brianza 31
I-20052 Monza
(Milano) (IT)
Applicant: **Michelotti, Marco**
Viale Brianza, 31
I-20052 Monza, (Milan) (IT)

(72) Inventor: **Michelotti, Leopoldo**
Viale Brianza 31
I-20052 Monza
(Milano) (IT)
Inventor: **Michelotti, Marco**
Viale Brianza, 31
I-20052 Monza, (Milan) (IT)

(74) Representative: **Marchi, Massimo et al**
c/o Marchi & Mittler s.r.l.
Viale Lombardia 20
I-20131 Milano (IT)

(54) **Shaped sheet article of polyethylene terephthalate and method for producing it.**

(57) An article of manufacture in the form of a shaped sheet, comprising
50-90% by weight of PET,
5-20% by weight of a "rubber",
10-45% by weight of an inert filler,
and having a crystallinity gradient such that said shaped sheet maintains the shape, under its own weight, up to
a temperature of at least 70°C and has impact strength which is substantially greater compared to that of the
fully crystallized shaped sheet.

EP 0 655 320 A1

The present invention relates to an article of manufacture in the form of a polyethylene terephthalate shaped sheet and a method for producing it. More particularly, it relates to a shaped sheet, for use mainly in building, which has different structural and mechanical properties at different depths of its thickness.

It is known that polyethylene terephthalate (PET) now constitutes the plastic material of choice for producing containers for drinks due to the fact that it does not release potentially toxic substances into the contents.

It is also known that current regulations do not allow the abovementioned containers to be reused.

Therefore large quantities of disposable PET containers are being accumulated.

In this description and the subsequent claims, the PET of the aforementioned disposable containers is indicated by the term "recycled PET".

The Italian Patent Application No. MI91-A-002949 filed on November 6, 1991 pointed out the uneconomical nature of the methods proposed to date for disposing of the abovementioned containers (incineration or depolymerisation and recovery of the monomers) and proposed recycling polyethylene terephthalate (PET) by extruding it into shaped sheets for building.

In particular, the abovementioned application proposed washing PET containers, crushing them and drying them thoroughly up to a moisture content of from 20 to 50 ppm. The resulting material was then crystallized, mixed with an inert mineral filler and extruded in flat sheets. Finally, the latter could be shaped in the form of corrugated sheets or other profiles, for example fretted, by conventional machines and techniques.

The shaped sheets obtained in this way were however found to be highly crystallized, with poor elasticity and low impact strength, a sheet with thickness of 3 mm breaking on the impact of a cylindrical striking mass, with spherical head and weighing 2 kg, from a height of only 0.2 m.

The Japanese Patent Application Opened No. 92,536/83 describes a biaxially-oriented plastic bottle comprising a bottom portion, a body portion, a shoulder portion and a neck portion formed by biaxially-oriented blow molding a parison of virgin polyethylene terephthalate, wherein said neck portion has a highly crystallized outer surface layer with density of no less than 1.36 g/cc, and a less crystallized inner surface layer with density of no more than 1.35 g/cc.

In order to achieve such crystallization the outer surface of the neck portion is heated at 180 °C for 30 seconds to 1 minute while the inner neck portion is maintained at a lower temperature.

However, when this procedure was utilized to manufacture a shaped sheet made from a blend of recycled PET and an inert mineral filler, unsatisfactory results were obtained (see Comparative Example 1).

It has now unexpectedly been found that, when producing shaped sheets, differentiated heat treatment provides good results only when an additive, capable of reducing the inclination of PET to crystallize when hot, is added to the blend of recycled PET and inert filler.

These additives are commonly known to the persons skilled in the art as "rubbers". Examples of "rubbers" are Paraloid™, of Rohm & Haas, Philadelphia (USA), and the blends of Lotader™ and of Lotryl™ of Elf Atochem S.A., Paris (France).

In the present description and in the claims the term "rubber" is therefore used to denote the abovementioned compounds as well as blends thereof and whatsoever other similar compound which is able to reduce the inclination of PET to crystallize when hot.

Generally the amount of "rubber" added to PET ranges from 3 to 25 parts by weight for 100 parts by weight of PET. It is preferably 5-10 parts by weight for 100 parts by weight of PET.

Another unexpected aspect of the present invention is that the shaped sheets produced with blends of recycled PET/rubber/inert filler become malleable and compliant at approximately 50-60 °C if, when they are produced, they are heated evenly (Comparative Example 3). On account of this undesirable characteristic they therefore tend to deform, under their own weight, and to collapse under the rays of the summer sun.

Contrarily if, after they are shaped, a certain degree of crystallization is produced in the first layers of their upper surface and the first layers of their lower surface are maintained as amorphous as possible, shaped sheets are obtained which do not deform, under their own weight, at temperatures of 70-75 °C and which have both good tensile strength and good elasticity at the flexure impact test.

It is therefore a first object of the present invention to provide an article of manufacture in the form of a shaped sheet comprising:

50-90% by weight of recycled PET and,

10-45% by weight of an inert filler,

characterized in that said shaped sheet contains 5-20% by weight of a rubber, has a crystallinity gradient such as to maintain its shape, under its own weight, up to a temperature of at least 70 °C and has an impact strength which is substantially greater compared to that of the fully crystallized shaped sheet.

In a preferred embodiment, a corrugated sheet 3 mm thick resists the impact of a 2 kg weight, having the striking portion in the shape of a ball with a diameter of 38 mm, when said corrugated sheet is placed on two supports 125 mm apart and is struck with an energy of approximately 15 joules on the lower portion of a corrugation of its side having higher crystallinity (ISO 6603/2).

5 The required crystallinity gradient of the shaped sheet according to the present invention is achieved by suitably heating the side wherein the highest crystallinity degree is to be promoted.

In an embodiment of the invention, the molten blend (about 250-280 °C) of recycled PET/rubber/inert filler which comes out of the extrusion die is transferred on a calender equipped with chill rolls, cooled by inner circulation of water having a low temperature (4-8 °C approximately), which shapes it to the required
10 thickness and width.

Preferably the width of the calendered tape is of from 50 to 200 cm. In turn the thickness is preferably of at least 2 mm. Typical examples of preferred thicknesses range from 2 to 7 mm and, even more preferably, from 2 to 4 mm.

After calendering and cooling, the tape is cut into shaped sheets having the required length. Preferably
15 said length is of from 100 to 1200 cm, even more preferably from 200 to 800 cm.

The thus obtained sheet is brought to a temperature (about 80-90 °C) suitable to shape it. Shaping, for example with a corrugated or fretted profile, is performed with conventional machines and techniques well known to those skilled in the art.

After having been shaped and, if necessary, cooled, the shaped sheet is heated substantially more on
20 one side than on the other.

This treatment is one of the most important phases of the present invention.

The more marked heating of one side, preferably the upper one, can be performed in various ways, for example by IR lamps or with a hot air stream. The upper side of the shaped sheet must preferably be heated to a temperature of over 120-140 °C. The time of heating will range depending on parameters which
25 are well-known to the persons skilled in the art, such as temperature, the thickness of the shaped sheet, the heating means used and the like.

For example, when the heat treatment is performed with hot air, the upper side of the shaped sheet may be exposed, for 1-5 minutes, to an air stream having a temperature of between 250-350 °C which laps it at a speed of a few metres per second, preferably at least 4 metres per second.

30 In this way, after the shaping phase, the configuration of the sheet is stabilised without jeopardising its impact strength. In fact, a corrugated sheet 3 mm thick treated in this way has impact strength of at least 15, preferably 20, joules and maintains its shape, under its own weight, up to temperatures of at least 70 °C, preferably 80-85 °C.

More particularly, in an embodiment of the present invention, the method comprises the following steps:

- 35 - washing and crushing of used PET containers,
- drying of said PET flakes up to a moisture degree of 50-20 ppm,
- preparation of a composition comprising 50-90% by weight of PET flakes, 5-20% by weight of a "rubber", 10-45% by weight of an inert filler,
- melting and extruding said composition into the form of a flat tape,
- 40 - cooling of said flat tape,
- cutting of the tape into flat sheets having the required length,
- shaping of said flat sheets at 80-90 °C according to a predetermined profile, and
- heating of the upper surface of said shaped sheets to promote a crystallinity gradient such that said shaped sheet maintains the shape, under its own weight, up to a temperature of at least 70 °C and
45 that it has an impact strength substantially greater compared to that of the fully crystallized shaped sheet.

Alternatively, the composition of the present invention may be extruded by means of a die suitably shaped so that it produces a flat tape having the required shape, thickness and width. Cooling, to at least 90 °C, must be as rapid and as efficient as possible, so that the tape maintains its shape until the
50 subsequent differentiated heat treatment. The other steps of processing are wholly equivalent to those already described above.

Therefore it is a further object of the present invention to provide a method for preparing a shaped sheet for building, said method comprising

- (a) washing and crushing of used PET containers,
- 55 (b) drying of said flakes of PET up to a moisture degree of 50-20 ppm,
- (c) the preparation of a composition comprising 50-90% by weight of said recycled PET flakes, 10-45% by weight of an inert filler,

(d) the production of shaped sheets according to conventional techniques, and
 (e) the differentiated heat treatment of said shaped sheets,
 characterized in that

(f) said composition also comprises from 5 to 20% by weight of a rubber,

(g) the abovementioned differentiated heat treatment consists of heating the upper surface of said shaped sheets to promote a crystallinity gradient such that said shaped sheet maintains the shape, under its own weight, up to a temperature of at least 70 °C and has substantially greater impact strength compared to that of the fully crystallized shaped sheet.

In the compositions of the shaped sheets according to the present invention, the inert filler is preferably a mineral filler.

Typical examples of inert mineral fillers well-known to the persons skilled in the art are calcium carbonate, talc, titanium dioxide, glass fibres and blends thereof.

Moreover, the compositions according to the present invention may also contain additives of a known type such as, for example, coloured pigments, flame retardants, UV ray absorbing agents and the like.

The following examples are intended to illustrate the present invention without, however, limiting it.

EXAMPLE 1

Blend composition:

70% by weight of recycled PET in the form of flakes obtained by cutting up bottles for mineral water,
 8% by weight of Paraloid EXL 3300, and
 22% by weight of calcium carbonate.

The abovementioned blend was dried up to a moisture degree lower than 50 ppm and then extruded in ICMA 170 double screw equipment of the firm ICMA, S. Giorgio su Legnano, Varese, Italy. The extrusion temperature was 250 °C.

From the outlet of the extrusion die, the molten mass was transferred to a calender having three chill rolls cooled with water at approximately 4 °C.

Thus flat sheets were obtained of the following dimensions: 720 x 1000 x 2.5 mm.

The abovementioned sheets were inserted in a continuous pilot tunnel system comprising four sections, each of which 1.4 m in length.

In the first section the sheets were heated with hot air to approximately 85-90 °C to make them deformable: the temperature of the heating air was approximately 125 °C.

In the second section the sheets were corrugated to dimensions of 177 x 51 mm while their temperature was maintained at approximately 85-90 °C with hot air.

In the third section the surface of the upper side of the corrugated sheets was lapped, for about 4 minutes, by an air stream heated to approximately 250 °C while the surface of its lower side was lapped by an air stream at room temperature (15-25 °C approximately).

In the fourth section the sheet was cooled with air at room temperature (15-25 °C approximately).

Chips approximately 0.1 mm thick were taken from a thus obtained shaped sheet at depths of 0, 1, 2 and 2.5 mm by milling slowly so as to avoid even a small rise in temperature.

The specimens were tested by differential calorimetric analysis with Mettler TA4000 apparatus to determine their crystallinity degree.

The results show that the crystallinity degree of the upper side is much greater than that of the lower side and that the intermediate layers have a degrading degree of crystallinity along the thickness of the shaped sheet, from the upper side to the lower one.

EXAMPLE 2

Blend composition:

80% by weight of recycled PET in the form of flakes obtained by cutting up bottles for mineral water,
 8% by weight of Paraloid EXL 3300, and
 12% by weight of calcium carbonate.

The procedure was the one described in Example 1 except that:

- the sheet was 3 mm thick;
- in the third section of the tunnel the temperature of the air conveyed onto the surface of the upper side of the corrugated sheet was 300 °C and the heating time was one and a half minutes approximately;

- in the third section of the tunnel the temperature of the air conveyed onto the surface of the lower side was 125 °C; and
 - in the fourth section of the tunnel the temperature of the cooling air was 20 °C approximately.
- The properties of the sheet obtained in this way are given in Table 1.

5

EXAMPLE 3

Blend composition:

- 79% by weight of recycled PET in the form of flakes obtained by cutting up bottles for mineral water,
- 3% by weight of Lotader™,
- 3% by weight of Lotryl™, and
- 15% by weight of calcium carbonate.

The procedure was the one described in Example 1 except that:

- the sheet was 3 mm thick;
- in the third section of the tunnel, the temperature of the air conveyed onto the surface of the upper side of the corrugated sheet was 300 °C and the heating time was one and a half minutes approximately;
- in the third section of the tunnel the temperature of the air conveyed onto the surface of the lower side was 125 °C; and
- in the fourth section of the tunnel the temperature of the cooling air was approximately 23 °C.

The properties of the sheet obtained in this way are given in Table 1.

COMPARATIVE EXAMPLE 1

Blend composition:

- 80% by weight of recycled PET in the form of flakes obtained by cutting up bottles for mineral water, and
- 20% by weight of calcium carbonate.

The procedure was the one described in Example 1 except that:

- the sheet was 3 mm thick;
- in the third section of the tunnel the temperature of the air conveyed onto the surface of the upper side of the corrugated sheets was 300 °C;
- in the third section of the tunnel the temperature of the air conveyed onto the surface of the lower side was 90 °C; and
- in the fourth section of the tunnel the temperature of the cooling air was 20 °C.

The properties of the sheet obtained in this way are given in Table 1.

COMPARATIVE EXAMPLE 2

The composition of Example 2 was processed as described in the same Example 2 except that the temperature of the air conveyed onto the surface of both the upper side and lower side of the corrugated sheets was 300 °C.

The properties of the sheet obtained in this way are given in Table 1.

COMPARATIVE EXAMPLE 3

The composition of Example 2 was processed as described in the same Example 2 except that the temperature of the air conveyed onto the surface of both the upper side and lower side of the corrugated sheets was 150 °C.

The properties of the sheet obtained in this way are given in Table 1.

TABLE 1

Flat Sheet											Corrugated Sheet									
Example	Density g/ml										Density g/ml					Hardness				
No.	U1	S1	M1	I1	U2	W	S2	M2	I2	DS	DI									
2	15	1.450	1.427	1.413	15	51	1.470	1.453	1.444	30	19									
3	15	1.465	1.452	1.448	15	51	1.476	1.458	1.452	35	16									
Comparative																				
Examples																				
1	10				5	30				42	42									
2	15	1.450	1.427	1.413	5	51				33	31									
3	15	1.450	1.427	1.413	15	10				22	16									

The codes of the above Table have the following meanings:

- U1 and U2 represent the impact strengths (expressed in joules) of the flat sheet and corrugated sheet respectively, determined by the ball drop test according to ASTM D648.
- S1 and S2 represent the densities of the upper layer of the flat sheet and corrugated sheet respectively, determined by hydrostatic scales at 23 °C.

- M1 and M2 represent the densities of the intermediate layer of the flat sheet and corrugated sheet respectively, determined by hydrostatic scales at 23 °C.
- I1 and I2 represent the densities of the lower layer of the flat sheet and corrugated sheet respectively, determined by hydrostatic scales at 23 °C.
- W represents the height in millimetres of the corrugation of the finished corrugated sheet after heating at 70 °C for 24 hours.
- DS and DI represent the hardness, expressed in kg/mm², of the upper and lower layers respectively of the corrugated sheet, determined measuring the area of the mark made by a steel sphere, having a diameter of 4 mm, under a load of 40 kg (Brinell test).

As can be seen from Table 1 above, the sheet according to the present invention (Examples 2 and 3) has impact strength both before and after corrugation (U1 and U2). Moreover, it maintains its shape even after heating at 70 °C for 24 hours (W). Further tests have demonstrated that it does not deform even after having been heated at 85 °C for 24 hours.

The sheet of Comparative Example 1 shows that the absence of rubber makes the sheet too fragile (U1 and U2) despite the differentiated heating. Moreover the sheet in Comparative Example 1 does not maintain its shape.

In the case of Comparative Examples 2 and 3, the composition of the sheet comprised a rubber but the corrugated sheet was not subjected to differentiated heat treatment.

In the flat state, the sheet had good impact strength (U1) both in the case of Comparative Example 2 and in the case of Comparative Example 3.

In the case of Comparative Example 2, heating of both the upper and lower sides of the corrugated sheet with air at 300 °C for approximately one and a half minutes reduced impact strength (U2) considerably.

Nevertheless, heating of both sides with air at 150 ° for one and a half minutes approximately (Comparative Example 3) did not have a negative effect on the impact strength of the corrugated sheet (U2) but the latter did not maintain its shape and collapsed after heating at 70 °C for 24 hours (W).

Claims

1. An article of manufacture in the form of a shaped sheet comprising 50-90% by weight of PET, 10-45% by weight of an inert filler, characterized in that said shaped sheet also comprises from 5 to 20% of a rubber, has a crystallinity gradient such as to maintain its shape, under its own weight, up to a temperature of at least 70 °C and has substantially greater impact strength compared to that of the fully crystallized shaped sheet.
2. An article of manufacture in the form of a shaped sheet according to claim 1, characterized in that the shaped sheet is a corrugated sheet, 3 mm thick, which resists the impact of a 2 kg weight, having the striking part in the shape of a ball with a diameter of 38 mm, when said corrugated sheet is placed on two supports 125 mm apart and is struck with an energy of approximately 15 joules on the lower portion of a corrugation of its side having higher crystallinity (ISO 6603/2).
3. An article of manufacture in the form of a shaped sheet according to claim 1 or 2, characterized in that the "rubber" is selected from the group comprising Paraloid™ EXL 3300 and the blends of Lotader™ and Lotryl™.
4. An article of manufacture in the form of a shaped sheet according to any one of claims 1 to 3, characterized in that the inert filler is a mineral filler selected from the group comprising quartz, calcium carbonate, talc, titanium dioxide, glass fibres and blends thereof.
5. An article of manufacture in the form of a shaped sheet according to any one of claims 1 to 4, characterized in that it further contains additives selected from the group comprising coloured pigments, flame retardants and UV ray absorbing agents.
6. An article of manufacture in the form of a shaped sheet according to any one of claims 1, 3, 4 or 5, characterized in that it has a thickness of at least 1 mm.

7. An article of manufacture in the form of a shaped sheet according to claim 6, characterized in that it has a thickness of 2-7 mm.
8. An article of manufacture in the form of a shaped sheet according to claim 6, characterized in that it has a thickness of 2-4 mm.
9. A method for preparing a shaped sheet for building, said method comprising:
 - (a) washing and crushing of used PET containers,
 - (b) drying of said flakes of recycled PET up to a moisture degree of 50-20 ppm,
 - (c) the preparation of a composition comprising 50-90% by weight of said recycled PET flakes, and 10-45% by weight of an inert filler,
 - (d) the production of shaped sheets according to conventional techniques, and
 - (e) the differentiated heat treatment of said shaped sheets, characterized in that
 - (f) said composition also comprises 5 to 20% by weight of a rubber,
 - (g) the abovementioned differentiated heat treatment consists of heating the upper surface of said shaped sheets to promote a crystallinity gradient such that said shaped sheet maintains the shape, under its own weight, up to a temperature of at least 70 °C and has substantially greater impact strength compared to that of the fully crystallized shaped sheet.
10. A method according to claim 9, characterized in that step (g) is performed with hot air.
11. A method according to claim 9, characterized in that step (g) is performed with IR lamps.
12. A method according to any of claims 9 to 11, characterized in that step (g) is performed by heating the upper surface of the shaped sheet to 120-140 °C.
13. A method according to any one of claims 9 to 12, characterized in that the rubber is chosen from the group comprising Paraloid™ EXL 3300 and the blends of Lotader™ and Lotryl™.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 94 20 3317

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
D,Y	PATENT ABSTRACTS OF JAPAN vol. 7, no. 189 (M-237) 18 August 1983 & JP-A-58 092 536 (TOUYOU SEIKAN KK) 1 June 1983 * abstract *	1-13	B29C71/00 B29B17/00 C08J11/06 C08L67/02 C08K3/00 //B29K67:00, B29K105:06, B29K105:26, B29L16:00
Y	EP-A-0 088 625 (E.I. DU PONT DE NEMOURS AND COMPANY) * page 11, line 30 - line 33; claims 1-18 *	1-8	
Y	EP-A-0 438 240 (ROHM AND HAAS COMPANY) * page 7, line 37 - page 10, line 54; claims 1,5,12-16 *	1,3-5, 9-13	
D,A	IT-A-912 949 (LEOPOLDO MICHELOTTI) * page 7, line 17 - line 23; claims 1-18 *	1-13	
A	EP-A-0 544 147 (BASF AKTIENGESELLSCHAFT) * the whole document *	1,3-5,9	TECHNICAL FIELDS SEARCHED (Int.Cl.6)
A	US-A-4 713 268 (WILLIAM G. CARSON) * claim 1 *	3,13	B29B C08J C08L B29C
A	EP-A-0 211 649 (E.I. DU PONT DE NEMOURS AND COMPANY) * column 3, line 1 - column 5, line 28; claims 1-14 *	3,13	
A	PATENT ABSTRACTS OF JAPAN vol. 14, no. 314 (C-0737) 5 July 1990 & JP-A-02 107 661 (MITSUBISHI RAYON CO LTD) 19 April 1990 * abstract *	3,13	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 1 March 1995	Examiner Van Nieuwenhuize, O
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 01.82 (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 94 20 3317

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	WO-A-92 03505 (E.I. DU PONT DE NEMOURS AND COMPANY) * page 7, line 29 - page 8, line 3 * * page 8, line 23 - page 10, line 21 * * page 17, line 19 - line 27 * ---	1,9-13	
A	EP-A-0 221 338 (BAYER AG) * claims 1-7 * ---	1,3-5,9	
A	US-A-4 693 941 (GEORGE J. OSTAPCHENKO) * the whole document * ---	1,3-5,9	
A	EP-A-0 185 103 (GENERAL ELECTRIC COMPANY) * page 16, line 1 - page 22, line 9 * * page 26, line 30 - page 28, line 10; claim 1 * ---	1,3,9,13	
A	PATENT ABSTRACTS OF JAPAN vol. 9, no. 142 (M-388) 18 June 1985 & JP-A-60 023 030 (TAKIRON KK) 5 February 1985 * abstract * ---	2,9	
A	FR-A-2 504 055 (NISSAN CHEMICAL INDUSTRIES CO., LTD.) * page 2, line 34 - page 3, line 27; claims 1-10; figures 10-15 * ---	2,9	
A	DE-A-16 04 740 (SUPERIOR CABLE CORPORATION) * page 3, last paragraph - page 4, paragraph 2 * ---	2,9	
A	NL-A-8 802 113 (STAMICARBON B.V.) * the whole document * -----	9	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 1 March 1995	Examiner Van Nieuwenhuize, O
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03.92 (P04C01)